

# deconex<sup>®</sup> MT 16



## Strongly alkaline cleaning agent

For parts cleaning in the manufacturing of medical devices



### Usage

The product is suitable for the cleaning of instruments and implants in the cleaning step:

- Intermediate cleaning

In interim cleaning, the product removes tough residues such as:

- Polishing pastes
- Processing brine
- Oil emulsions

### Properties

deconex<sup>®</sup> MT 16 is:

- Free of corrosion protection agents
- Free of perfumes
- Free of dyes

The product is also:

- Phosphate-free
- Chlorine-free
- Biologically easily degradable

### Ingredients

- Surfactants
- Chelating agents
- Alkali

### Application

The following application conditions have been found to be effective in practice:

Cleaning	Dosage	Temperature	Exposure time
Use in interim cleaning in spraying systems	0.5-2%	55-75 °C	3-10 min
Use in interim cleaning in ultrasound systems	1-5%	50-75 °C	5-15 min

This product is low-foaming from 53°C.

The process parameters (time, concentration, temperature) must be adjusted to the parts/materials to be cleaned.

# deconex® MT 16

## Instructions for use

For optimum use in spraying systems, the following is recommended:

- Prevent rinsing shadows. (Check loading)
- Use deconex® MT 32 afterwards for optimum rinsing performance
- Use demineralised water for final rinsing

For optimum use in ultrasound systems, the following is recommended:

- Prevent the formation of air bubbles in hollow spaces and shadowing of the ultrasound. (Check loading)
- Use deconex® MT 32 afterwards for optimum rinsing performance
- Use demineralised water for final rinsing

Adjust the ultrasound power level to the process conditions and system details. It should be at least 10 watts/litre.

Always immerse substrates fully in the cleaning bath.

Not suitable for aluminium and materials sensitive to alkaline chemicals.

## Chemical-physical data

pH value	1% in demineralised water	approx. 12.7
Density	Concentrate	1.29 g/mL
Appearance	Concentrate	clear, yellow

## Additional information

Information regarding safety in the workplace, storage and disposal / waste water can be found on the safety data sheet for this product.

Locally applicable waste water and disposal regulations must be complied with.

Benefit from our expertise! Ask us for practical information about your specific application.

Foam-free from about 55 °C. To prevent foaming, the product should only be added to water above this temperature.

For professional use only.

To meet the strictest requirements of the medical device industry, we recommend using the product in demineralised water.

## Material compatibility

Suitable for:

- Stainless steel
- Pure titanium
- Co-Cr-Mo
- UHMW-PE
- PEEK
- Fibre composite materials
- Bioceramics

## Delivery

Please ask your representative regarding current container sizes.

Containers, screw caps, seals and labels are made from recyclable polyethylene.

## Manufacturer:

### Borer Chemie AG

Gewerbstrasse 13, 4528 Zuchwil / Switzerland  
Tel +41 32 686 56 00 Fax +41 32 686 56 90  
office@borer.ch, www.borer.swiss

All information provided is based on our knowledge as it currently stands, however it does not constitute any guarantee of product properties and does not form the basis of any legal relationship.